

## TEST REPORT

KOTITI No : 8220-1509-101501-001 Issue No : 1378314705

Receipt Date : 06 / 07 / 2020 Issue Date : 17 / 07 / 2020

Sample Name	KA100N 2 Grade	Test Object	Research/Reference/Etc
Lot No.	-	MDF/MFG	02 / 07 / 2020
Weight/Volume	-	Expiry Date	-
Company	CNTUS SUNGJIN CO., LTD	President	HA CHOON WOOK
Address	24, Noksansaneopjung-ro 192beon-gil, Gangse o-gu, Busan, Republic of Korea	Telephone	82-31-642-6401

## Test Item & Test Result

Test Item	Test Standards		Unit	Result		Test Method	
Shape test	Main body(width)	124 ± 10	mm	Main body(width)	124		
	Main body(height)	155 ± 10		Main body(height)	153	Client Method	
	Headband(left)	180 ± 18		Headband(left)	175		
	Headband(right)	180 ± 18		Headband(right)	185		
Filtering efficiency(NaCl)	≧ 80		%	Before pretreatment : 100/100/100 After pretreatment : 100/100/100		MFDS Guideline	
Facial Inhalation resistance	≦ 60		Pa	Before pretreatment : 21/18/21 After pretreatment : 21/22/21		MFDS Guideline	
Tensile strength	≧ 10		N	24		MFDS Guideline	

Researcher: Yoon Sub Cho, A Yeong Kwon Technical Manager: Hae Sung Kim

- $\ensuremath{\mathbb{X}}$  The test results above shall be only subject to the requested test items.
- In the case of insufficient space on the page, test items and test results may be written in the appendix.
- When advertising test results or indicating test results on containers or packages, the entire content of the test report shall be indicated.
- \* This report produced in relation to the services will not be related with MFDS. And MFDS in not legally liable.

## **KOTITI Testing & Research Institute**

