Decorplate

REPLASA / RECUBRIMIENTOS PLÁSTICOS

We recognise our clients through innovation and commitment, as they take us to the top every day.

Decorplate



General characteristics


It offers decorative solutions in a great variety of finishes, respecting aluminium and steel flexibility and folding properties.

General properties

- Great decorative possibilities in one-colour finishes or RAL, prints or wood style.
- \cdot Good resistance to stains, cleaning products and corrosion.
- \cdot Great resistance to corrosion and dampness.
- \cdot High folding flexibility.
- \cdot Easily mechanised, but cannot be welded.
- Great possibilities for offset printing.

Composition

- Ο Protective film 30-50 μ (optional)
- PVC film 110-200 μ
- Adhesive 7-10 μ
- Metallic substrate
 - \cdot Galvanised steel according to EN 10346 standard
 - \cdot Cold laminated steel according to EN 10131 standard
 - \cdot Aluminium according to EN485 standard
- Back primer 5-10 μ (optional)



Product behaviour

DESCRIPTION	TEST	UNIT	RESULT	OBSERVATIONS
• Total coating thickness	ECCA T1	μ	110-200	depending on film type
• Specular gloss (Gardner 60°)	ECCA T2	%	10±5	depending on film type
Colour difference	ECCA T3		∆E <1−1,5	depending on film reference
• Pencil hardness	ECCA T4		H-2H	
Resistance to quick deformation	ECCA T5	joules	18	without detachment
Adherence after Erichsen cupping	ECCA T6	mm	8	without detachment
• T bending	ECCA T7		оТ	no cracking
Resistance to salt spray	ECCA T8	hours	>600	2 mm max. detachment
Resistance to water immersion	ECCA T9	hours	500	2 mm max. detachment
• Resistance to accelerating Xenotest ageing test	ECCA T10	hours	>500	E<1
• Heat ageing	ECCA T13	hours	500	120° C: no alteration
Resistance to Taber abrasion	ECCA T16	mg	<20	1000 cycles
• Stain resistant	ECCA T18			
Strawberry, orange, butter, fried tomato, mustard, lipstick, oil, milk, coffee, tea, chocolate and soap.			stain free	after 16 hours

Recubrimientos Plásticos S.A. Autovía A-12, salida 9 E-31190 Astrain (Navarra) Spain Tel.: +34 948 353 015 Fax: +34 948 353 122

www.replasa.es

Decorplate

Acquaplate Aluplate Astraplate Colorplate Glossyplate Inoxplate Lamiplate Metalplate Starplate Thermoplate



